



TONON

made in Italy www.tononitalia.com

Moss

category 4






4MA



4MB



4MC



4MD



4ME



4MF



4MG

Composition	100%PES FR	
Width	175 ± 2%	
Linear Weight	854 gr/ml ± 5%	
Seam slippage resistance <small>EN ISO 13936/2</small>	WARP	WEFT
	1,7	2,5
Abrasion Resistance	End Point (A) Fully worn off (B) <small>EN ISO 12947/2</small>	
	50.000 (A)	
Pilling resistance <small>EN ISO 12945/2</small>	Change aspect 3000c <small>EN ISO 12947/4</small>	
	3-4	
Assessment of ignitability	BS5852 Sche. Part 4 Source 0 / 1 BS7176 Low hazard EN 1021 Part 1 / 2 UNI 9175 IM Clase 1.IM CAL TB 117:2013 NFPA 260:2013 DIN 4102 B2 NF D 60 013 IMO FTB 2010 Part 8 A 652 (16) NF P-92:507 M1	
	PASS	
Lightfastness <small>EN ISO 105-B02</small>	6-7	
Colour fastness to rubbing <small>EN ISO 105-X12</small>	DRY	WET
	5	4-5
Dimensional change in domestic washing and drying <small>EN ISO 3759 / EN ISO 6330 / EN ISO 5077</small>	WARP	WEFT
	-3%	1,5%
Acoustic test sound absorption	EN ISO 354:2004 EN ISO 11654:1998 ASTM C423	
Cleaning		

TONON
made in Italy www.tononitalia.com

Tonon & C. spa
Via Diaz 22 33044 Manzano Italy
Tel. +39 0432 740740 Fax +39 0432 740770
www.tononitalia.com tonon@tononitalia.it